

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets

Patent widerrufen!
13. 1995



Publication number: **0 304 162 B1**

12

EUROPEAN PATENT SPECIFICATION

(D1)

45 Date of publication of patent specification :
05.06.91 Bulletin 91/23

51 Int. Cl.⁵: **F16C 9/04**

21 Application number : 88306513.8

dt. Übers. f. Hekt

22 Date of filing : 15.07.88

54 Split bearing assemblies, method for making.

30 Priority : 17.08.87 US 85687

73 Proprietor : GENERAL MOTORS CORPORATION
General Motors Building 3044 West Grand Boulevard
Detroit Michigan 48202 (US)

43 Date of publication of application :
22.02.89 Bulletin 89/08

45 Publication of the grant of the patent :
05.06.91 Bulletin 91/23

72 Inventor : Hekman, Frederick Allen
1293 Hampton
Grosse Pointe Woods Michigan 48236 (US)

84 Designated Contracting States :
DE FR GB IT

74 Representative : Haines, Arthur Donald et al
Patent Section Vauxhall Motors Limited 1st Floor Gideon House 26 Chapel Street
Luton, Bedfordshire LU1 2SE (GB)

56 References cited :
EP-A- 0 167 320

(hyg.)
Die beiden Abstützungsw. 58 können nach beiden Seiten ausweichen
(Bei H nur einseitige Abstützung des Deckels)

Vorne der des Verbiegens

H: der Hauptkörper wird überhaupt nicht gehalten (zurückgehalten)

beide Seiten sind mit Klappen gehalten. Daher kein Verbiegen obwohl sie

Note : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 304 162 B1

kurz hintereinander brechen!

Description

Technical Field

This invention relates to methods for making split-bearing assemblies of the type comprising a main body and a separable cap which are secured together to define a journal-encircling bearing, or bearing-receiving opening, for supporting, for example a journal of a rotatable shaft. More particularly, the invention relates to fracture-separation methods for making split-bearing assemblies of the type described.

Background

EP-A-0 167 320 extensively describes prior methods of making split-bearing assemblies for various uses. Examples of such uses are for engine crankshaft main and connecting rod bearing assemblies, camshaft bearing assemblies, crank-supporting bearing assemblies for compressors, presses and other machines, and other rotatable shaft-supporting bearing assemblies, in all of which a removable saddle-like bearing cap is secured to a mating saddle-like main body to provide for the installation and removal of a rotatable shaft, an attached connecting rod, or another device.

EP-A-0 167 320 further refers to prior methods of forming the main body and cap as integral members and completely machining all necessary surfaces, including the journal-encircling opening or bore, before separating the main body and cap members. The members are then separated by material-fracture techniques which involve fracturing the components along predetermined fracture planes, leaving interlocking rough surfaces that are capable of being re-engaged for assembly of the components into an operating assembly.

The prior art fracture techniques are said to include various methods of weakening the separation planes, such as by drilling holes therein and/or providing weakening notches along one or more edges. Embrittlement of the material in the separating planes may also be provided for either by material selection, heat treatment (including hardening of various types), or by freezing the material to reduce its temperature below the embrittlement point.

Further, EP-A-0 167 320 suggests that the various types of prior fracture techniques introduce various problems, among which are reduction of the engageable surface area of the separated parts that reduces the allowable clamping load and, in some cases, the introduction of excessive bending of the separating parts which results in yielding deformation of metal along the edges that interferes with proper reassembly of the separated components. Deformation of the previously machined opening can also

be a problem with some methods.

EP-A-0 167 320 proposes a two-step fracture-separation method which avoids deformation of the fractured material at the edge of the last-broken legs of the bearing assembly. This method includes, first, fracturing one of the pairs of integrally-formed legs and, then, restraining the fractured legs from moving substantially away from their mated positions, by, for example, clamping, whilst fracturing the other pair of integrally-formed legs. The fracture steps are accomplished in each instance by placing the split planes in tension, such as by applying a separating force in the bore between the cap and body.

Summary of the Invention

The present invention utilizes the basic principles of the fracture-separation methods disclosed in EP-A-0 167 320 but applies them in a manner and/or with certain modifications not specifically disclosed or suggested in EP-A-0 167 320. Like that of EP-A-0 167 320, the present method relies upon pre-forming of an integral bearing assembly, such as a connecting rod which may be completely machined and is made sufficiently brittle, and performing fracture-separation whilst preventing substantial rotation of the cap relative to the body during separation of the second-to-be-fractured pair of legs. Also, the method is believed to inherently follow the steps taught by EP-A-0 167 320 of, first, fracturing one of the integral pairs of legs by causing tension across the split plane and, second, clamping the partially separated cap and body portions to prevent substantial rotation of the cap relative to the body whilst fracture-separation of the second pair of legs is carried out by causing tension on the split plane thereof.

The present method provides certain steps or procedures for carrying out the method of EP-A-0 167 320 which are not specifically suggested or pointed out therein and thus constitutes an improvement thereof. Thus, in the present method, the integral cap and body are firstly clamped in separable anti-rotation clamp means that limit the relative motion of the cap and body to linear separating motion and secondly the integral pairs of legs are fractured by moving, preferably sharply, the cap and body clamp means linearly apart whilst preventing relative rotation therebetween, thereby tensioning both pairs of integral legs across the split lines thereof and causing fracture-separation of both pairs of legs in the same motion.

Whilst the present method differs in detail from the procedures specifically pointed out in EP-A-0 167 320, it is, nevertheless, submitted that this method inherently carries out the basic steps prescribed in that Patent qualification. Even though the fracture step takes place in one motion in which tensile forces are applied to both pairs of legs, it is inherent that one of the pairs of legs will crack first. After this, however,

unlike the method disclosed in EP-A-0 167 320, the clamped condition of the cap and body to prevent the relative rotation thereof will maintain the fractured legs in essentially the mated positions thereof until, a fraction of a second later, the second pair of legs is fractured and the cap is physically separated from the body.

In developing the present method for the manufacture of engine connecting rods, it has been preferred to make the integral workpieces by forging and to use starting notches in the bores at the split planes to initiate the fractures as is taught in EP-A-0 167 320. Embrittlement of the workpieces in a cryogenic liquid nitrogen bath prior to fracture-separation has also been included in the method.

Additionally, however, it has been found preferable to make the workpieces from material having a fine grain size and homogeneous microstructure as this reduces the possibility of flaking and provides cleaner breaks at the fracture planes. This may be accomplished in the initial selection of materials and aided by heat treatment if required.

Also, it is preferred, when using steel forgings pre-machined with threaded cap screw or bolt openings, to provide small breakout openings drilled into the screw or bolt openings at the split planes on the outer sides, opposite to the starter notches in the bore. This provides a terminating line for each fracture as it proceeds from the starter notch around both sides of the screw or bolt opening to the breakout opening. It thus prevents the occurrence of a jagged edge where the two sides of the fracture meet at what may be slightly differing levels without the controlling action of the breakout opening.

The various features and advantages of the method will be more completely understood from the following description taken together with the accompanying drawings.

Brief Drawing Description

In the drawings :

Figure 1 is a plan view of a crankpin-encircling end of a connecting rod, forming a split-bearing assembly in accordance with the invention ;

Figure 2 is a side view of the connecting rod portion of Figure 1 ;

Figure 3 is a fragmentary, transverse cross-sectional view from the plane indicated by the line 3-3 of Figure 2, showing a cap-securing means and breakout openings ;

Figure 4 is a cross-sectional view of the assembly at the fracture planes as indicated by the line 4-4 of Figure 1

Figure 5 is a fragmentary plan view showing the partial fracture-separation of a connecting rod which momentarily occurs during the fracture-separation process ;

Figure 6 is a plan view of a connecting rod work-piece clamped in apparatus for conducting fracture-separation of the cap and body by the method of this invention, and

Figure 7 is a longitudinal cross-sectional view of the apparatus from the plane of the line 7-7 of Figure 6.

Detailed Description

Figures 1-4 of the drawings illustrate the crankpin-encircling large end of a connecting rod assembly generally indicated by numeral 20 and of the type for use, for example, in internal combustion engines. Connecting rod 20 includes a saddle-like main body 21 which is bifurcated to form first and second legs 22, 24 respectively and a removable saddle-like bearing cap 25 that is also bifurcated to define first and second legs 26, 28, respectively. The first legs 22, 26 of the body and cap have mating ends 29, 30 respectively and the second legs 24, 28 of the body and cap have mating ends 32, 33, respectively.

The mating ends 29, 30 and 32, 33 are secured in end-to-end engagement so that the saddle-like members 21, 25 define a journal-receiving opening 34 in which a crankpin journal, not shown, may be received. Commonly, split-insert bearing shells, not shown, are clamped within the journal-receiving opening 34 to provide a suitable bearing surface for relative rotation of a crankpin, not shown, within the connecting rod.

As shown, the bifurcated legs 22, 24, 26, 28 of the body and cap incorporate integral bolt bosses through which bolt openings 36 extend from the distal ends of the cap legs 26, 28 through the mating ends 29, 30, 32, 33 and into the legs 22, 24 of the body to receive body bolts 37 that threadably engage the legs 22, 24 of the body and secure the legs 26, 28 of the cap in engagement therewith. Alternatively, unthreaded through openings receiving conventional bolts and nuts could be used to secure the cap legs to the body.

The mating ends 29, 30 and 32, 33 of the legs of the cap and body are comprised of rough, uneven mating surfaces formed by the fracture-separation methods to be subsequently described and lying generally along split planes 38, 39 located on opposite sides of the opening 34. In the present instance the split planes lie on a common transverse diametral plane passing through the axis 40 of the journal-receiving opening 34 and at right angles to the main longitudinal axis 41 of the connecting rod. It would be possible, however, to form the split planes 38, 39 outside of, or at angles to, the diametral plane.

At the inner edges of the mating ends, along the split planes 38, 39, notches 42, 44 are formed in the periphery of and extending longitudinally for the length of the cylindrical opening 34 to initiate and locate the starting points of separation in the subse-

quent fracture steps and form the inner edges of the mating legs of the cap and body. In the outer portions of the mating legs, breakout holes 45 are drilled or otherwise formed normal to and intersecting the bolt or cap screw openings 36 in the split planes 38, 39 and centred on the sides of the legs opposite the starter notches 42, 44. The cap may be formed of any suitable material such as cast iron, steel or aluminium, however forged steel is presently preferred as will be subsequently more fully discussed.

The steps in a preferred form of method, according to the invention, for manufacturing the connecting rod assembly of Figures 1-4 are as follows :

An integral unfinished connecting rod 20, including unseparated body and cap portions, 21, 25, respectively, with a journal-receiving opening defined thereby, is first formed in any suitable manner, such as, for example, by casting, or by forging.

The integral rod is then machined to essentially its finished dimensions by machining the bore 34 (preferably leaving a small amount of material for final machining after fracture-separation), drilling and threading the bolt openings 36 and, if needed, breakout holes 45 and finishing the opposite sides of the connecting rod at the ends of the bore 34, if desired. Preferably, notches 42, 44 are also machined (or otherwise formed by methods such as casting or forging) extending longitudinally along the opposite lateral sides of the bore 34.

Following machining, preparation is made for separating the bearing cap 25 from the main body 21. For this purpose, the material, at least that in the split planes 38 and 39, must be sufficiently brittle. If the material of the connecting rod is inherently brittle, such as cast iron and some aluminium alloys, no additional preparation may be required. Less brittle materials, such as steel, may require selective hardening by any suitable process to embrittle the material sufficiently along the split planes to avoid excessive yielding when fractured.

As a third alternative, ductile or insufficiently brittle materials may be made temporarily brittle for processing purposes by reducing the temperature to a sufficiently low level. This may be done, for example, by soaking the parts in liquid nitrogen until they approach the liquid temperature of -196°C (-320°F) (or at least reach a temperature level of -101°C (-150°F), in preparation for the fracturing step. With forged steel materials, heat treatment to control grain size and homogeneity may also be appropriate.

When the material along the split planes is, or has been made, sufficiently brittle, force-applying means are utilized to apply a separating force on opposite sides of the bore 34, acting outwardly in opposite directions parallel to the longitudinal axis 41 of the connecting rod, as shown by the arrows in Figure 5 of the drawings. The application of force in this manner causes tension across the split planes extending out-

wardly from the notches on opposite sides of the opening 34. The tension causes a crack 46 to progress from the edge of either one of the notches, in this case 44, generally along its normal split plane 39 to the outer edge of the connecting rod integral legs, terminating on the sides 64, 66 of the breakout opening 45, if provided, and causing fracture-separation of the associated pair of the mating legs, in this case 24 and 28, whilst forming their mating ends as previously described.

After cracking of the one pair of legs has occurred, continued force application along the connecting rod longitudinal axis, causing further expansion of the opening 34, would cause the formation of a second crack along the split plane 38, on the opposite side of the connecting rod and result in fully separating the cap and main body. However, experience has shown that completing the fracture in this manner without additional controls may, through relative rotation of the cap and body, cause excessive bending of the material at the outer edges of the mating legs defined by the second crack. This bending may result in deformation or uncontrolled multiple fractures of the material along the outer edge which can interfere with proper mating engagement of the cap and main body upon attempted re-assembly of the two members. Thus, it is advisable to provide means to prevent excessive opening of a space in the crack 46 which would allow the development of bending stresses in the material at the outer edge of the opposite split plane.

This may be accomplished by the method of the present invention carried out by suitable means as are shown in Figures 6 and 7. The integral connecting rod workpiece 20 is secured within a fixture generally indicated by numeral 50. The fixture 50 includes a body clamp assembly 51 and a cap clamp assembly 52 relatively movable along longitudinally-aligned ways 54 in linear separating and approaching motions. A fracture ram 55 is arranged to provide rapid separation of the two clamp assemblies.

The body clamp assembly 51 includes a semi-circular pilot 56 which engages the body half of the journal opening 34 and a pair of body clamp elements 58 that, when actuated, engage the legs 22, 24 of the body and clamp the body non-rotatably against the pilot 56 thereof. Similarly, the cap clamp assembly 52 includes a semi-circular pilot 59 which engages the cap half of the journal opening 34 and a cap clamp element 60 that, when actuated, engages the legs 26, 28 of the cap and clamps the cap non-rotatably against the pilot 59 thereof.

The fracture ram 55 includes a wedge 62 that, when drawn downwards by an impact mechanism, not shown, acts against angled sides 63 of recesses in the pilots 56, 59 and forces apart the pilots and their associated clamp assemblies. This quickly separates the cap linearly from the body by causing tension at

the split planes 38, 39 between the pairs of integral legs 22, 26 and 24, 28 until they fracture as described previously and in EP-A-0 167 320.

Even though the fracture process is accomplished in a single motion of the fracture apparatus, the method inherently results in one of the pairs of legs being the first to fracture. Thereafter, the clamping means, by preventing relative rotation of the cap and body and requiring the separation thereof to be essentially linear, maintain the first fractured legs in essentially their mated positions until the fracture of the second pair of legs is accomplished. This may only take a fraction of a second. The separation of the completely fractured parts then continues until the separating step is complete.

In carrying out the fracture process, it should be recognized that the clamping step may be accomplished in other ways than by applying a clamping force on the ends of the separated legs as described in the specification. Accordingly, any method whereby the legs of the first separated pair are maintained essentially in their mated positions is to be considered as falling within the term "clamping".

In accordance with the present invention, it has been found that when forged steel workpieces are used, as is presently preferred, material selected and treated to have a homogeneous fine grain structure is preferred. This reduces the possibility of flaking and provides cleaner breaks at the fracture planes.

Also, it is preferred, when using forged steel workpieces provided with screw or bolt openings, to provide the small breakout openings 45 drilled into the screw or bolt openings 36 at the split planes on their outer sides, opposite to the starter notches 42, 44 in the journal opening 34. The breakout openings 45 provide terminating lines for the fractures as they proceed from the starter notches 42, 44 around both sides of the screw openings 36 to the breakout openings 45. They thus prevent the occurrence of jagged edges where the two sides of the fractures meet at what may be slightly differing levels without the controlling action of the breakout openings.

Claims

1. A method of making a split-bearing assembly (20) having a saddle-like main body (21) with first and second legs (22, 24) and a removable saddle-like bearing cap (25) with first and second legs (26, 28) having ends (29, 32) respectively secured in end-to-end engagement with mating ends (30, 33) of the first and second legs (22, 24) of said body (21) to define a journal-receiving opening (34), said method comprising initially forming the bearing assembly body (21) and cap (25) integral with the mating leg ends (29-30, 32-33) thereof integrally joined together, said integral body and cap being in a relatively brittle con-

dition, at least along generally predetermined split planes (38, 39) defining the leg ends on opposite sides of said opening (34), said body (21) and said cap (25) having essentially their assembled final dimensions, with said opening (34) being centred on an axis (40) lying within said main body (21) and said cap (25), generally between said split planes (38, 39), and separating the cap (25) from the main body (21) by fracturing the integral legs (22-26, 24-28) generally along said split planes (38, 39) on opposite sides of said opening (34) to form said legs (26, 28, 22, 24) of the saddle-like cap (25) and body (21), said first and second legs of the cap (25) and body (21) comprising respectively first and second pairs mateable along said split planes (38, 39), wherein the fracturing step is accomplished by causing tension across the split planes (38, 39) of said integral legs by forcing the cap (25) and main body (21) longitudinally apart to fracture and separate the ends (29-30, 32-33) of the legs of said pairs at their respective split planes whilst restraining said cap (25) and main body (21) against undue movement, characterised in that the method includes, prior to the fracturing step, restraining the integral bearing assembly within a fixture (50) so that any substantial movement of said cap (25) relative to said body (21) can only occur in a direction along an axis extending at right angles to said split planes (38, 39); and the fracturing step is accomplished by forcing the cap (25) and the main body (21) linearly apart whilst continuously restraining said cap (25) and the main body (21) against any substantial relative rotation, thereby fracturing and separating the ends of both of said pairs of integral legs at the respective split planes (38, 39) thereof in one essentially linear separating motion of the cap (25) from the main body (21), thereby avoiding any bending of the legs at the split planes and producing mating fracture surfaces (29-30, 32-33) on engaging edges of the legs to provide the capability of mating re-assembly, without substantial dimensional changes thereof.

2. A method of making a split-bearing assembly (20) according to claim 1, in which said step of forcing the cap (25) and the main body (21) linearly apart is accomplished by applying separating forces to the body (21) and cap (25) in directions normal to a plane joining the split planes (38, 39) of the two pairs of legs, said forces being applied to opposite sides of said opening (34), between the legs of the body (21) and of the cap (25).

3. A method of making a split-bearing assembly (20) according to claim 1 or 2, in which longitudinal notches (42, 44) are provided across inner edges of the split planes (38, 39) on opposite sides of the opening (34) prior to the fracturing step, to initiate the fracture and positively locate inner edges of the separated leg ends (29, 30, 32, 33).

4. A method of making a split-bearing assembly (20) according to any one of the preceding claims, in

which the integral legs are provided with fastener openings (36) extending from the cap (25) into the body (21) on opposite sides of the opening (34), and breakout holes (45) are provided extending outwards along the split planes from the fastener openings (36) through outer edges of the integral legs to provide predetermined termination locations for the subsequent fracture surfaces (29, 30, 32, 33).

5. A method of making a split-bearing assembly (20) according to claim 1, in which said split bearing assembly (20) comprises a connecting rod assembly.

6. An apparatus for carrying out a method according to any one of claims 1 to 5, characterised in that said apparatus comprises a fixture (50) including a body clamp assembly (51) and a cap clamp assembly (52) relatively movable to one another along longitudinally-aligned ways (54) in linear separating and approaching motions, and a fracture ram (55); said body clamp assembly (51) comprises a semi-circular pilot (56) engageable with a body half of said journal-receiving opening (34), and a pair of body clamp elements (58) that, when actuated, engage the legs (22, 24) of the body (21) to clamp the body non-rotatably against said pilot (56); said cap clamp assembly (52) comprises a semi-circular pilot (59) engageable with a cap half of said journal-receiving opening (34), and a cap clamp element (60) that, when actuated, engages the legs (26, 28) of the cap (25) to clamp the cap (25) non-rotatably against said pilot (59); and said fracture ram (55) includes a wedge (62) which, when driven by an impact mechanism, acts against angled sides (63) of recesses in the pilots (56, 59) to quickly separate the cap (25) linearly from the body (21).

Ansprüche

1. Verfahren zur Herstellung einer geteilten Lageranordnung (20) mit einem sattelartigen Hauptkörper (21) mit ersten und zweiten Schenkeln (22, 24) und einem abnehmbaren sattelartigen Lagerdeckel (25) mit ersten und zweiten Schenkeln (26, 28) die Enden (29, 32) besitzen, die jeweils in Endanlage mit passenden Enden (30, 22) der ersten und zweiten Schenkel (22, 24) des Körpers (21) angebracht sind, um eine Lagerzapfen-Aufnahmeöffnung (34) zu bestimmen, wobei das Verfahren umfaßt das anfängliche Bilden des Lageranordnungs-Körpers (21) und des Deckels (25) integral mit den passenden Schenkeln (29-30, 32-33) derselben, die integral miteinander verbundenen sind, wobei die integralen Körper und Deckel in einem relativ zerbrechlichen Zustand sind mindestens längs allgemein vorbestimmter Teilungsebenen (38, 39), welche die Schenkeln an einander gegenüberliegenden Seiten der Öffnung (34) bestimmen, der Körper (21) und der Deckel (25) im wesentlichen ihre endgültigen Zusam-

menbauabmessungen besitzen, mit der Öffnung (34) zentriert an einer Achse (40), die innerhalb des Hauptkörpers (21) und des Deckels (25) allgemein zwischen den Teilungsebenen (38, 39) liegt, und das Abtrennen des Deckels (25) von dem Hauptkörper (21) durch Brechen der integralen Schenkel (22-26, 24-28) allgemein längs der Teilungsebenen (38, 39) an gegenüberliegenden Seiten der Öffnung (34) zum Ausbilden der Schenkel (26, 28, 22, 24) der sattelartigen Deckel (25) und Körper (21), wobei die ersten und zweiten Schenkel des Deckels (25) und des Körpers (21) jeweilige erste und zweite Paare umfassen, die längs der Teilungsebenen (38, 39) anpaßbar sind, und der Schritt des Brechens durchgeführt wird, indem Zugspannung über die Teilungsebenen (38, 39) der integralen Schenkel hervorgerufen wird durch Abdrücken des Deckels (25) und des Hauptkörpers (21) in Längsrichtung voneinander zum Brechen und Trennen der Enden (29-30, 32-33) der Schenkel der Paare an ihren jeweiligen Teilungsebenen, unter Zurückhalten des Deckels (25) und des Hauptkörpers (21) gegen eine unzulässige Bewegung, dadurch gekennzeichnet, daß das Verfahren vor dem Schritt des Brechens enthält das Zurückhalten der integralen Lageranordnung innerhalb einer Aufspannvorrichtung (50) in der Weise, daß eine wesentliche Bewegung des Deckels (25) gegenüber dem Körper (21) nur in einer Richtung längs einer Achse auftreten kann, die sich im rechten Winkel zu den Teilungsebenen (38, 39) erstreckt; und daß der Schritt des Brechens durchgeführt wird durch lineares Auseinanderdrücken des Deckels (25) und des Hauptkörpers (21) unter andauerndem Zurückhalten des Deckels (25) und des Hauptkörpers (21) gegen jede wesentliche Relativverdrehung, wodurch die Enden beider Paare integraler Schenkel an den jeweiligen Teilungsebenen (38, 39) derselben in einer im wesentlichen linearen Trennbewegung des Deckels (25) von dem Hauptkörper (21) gebrochen und getrennt werden, um dadurch jedes Verbiegen der Schenkel an den Teilungsebenen zu vermeiden und passende Bruchflächen (29-30, 32-33) aneinander anliegenden Kanten der Schenkel zu erzeugen und die Möglichkeit eines passenden Wiederzusammenfügens ohne wesentliche Maßänderungen derselben zu schaffen.

2. Verfahren zur Herstellung einer geteilten Lageranordnung (20) nach Anspruch 1, bei dem der Schritt, den Deckel (25) und den Hauptkörper (21) linear voneinander wegzudrücken, durchgeführt wird durch Anlegen von Trennkräften an den Körper (21) und den Deckel (25) in auf einer der Teilungsebenen (38, 39) der beiden Schenkelpaare verbindenden Ebene senkrechten Richtungen, wobei die Kräfte an einander gegenüberliegende Seiten der Öffnung (34) zwischen den Schenkeln des Körpers (21) und des Deckels (25) aufgebracht werden.

3. Verfahren zur Herstellung einer geteilten

Lageranordnung (20) nach Anspruch 1 oder 2, bei dem Längsnuten (42, 44) über die inneren Kanten der Teilungsebenen (38, 39) an einander gegenüberliegenden Seiten der Öffnung (34) vor dem Schritt des Brechens geschaffen werden, um das Brechen einzuleiten und zwangsweise Innenkanten der getrennten Schenkelenden (29, 30, 32, 33) festzulegen.

4. Verfahren zur Herstellung einer geteilten Lageranordnung (20) nach einem der vorangehenden Ansprüche, bei dem die integralen Schenkel mit Befestigeröffnungen (36) versehen werden, die sich an gegenüberliegenden Seiten der Öffnung (34) von dem Deckel (25) in den Körper (21) erstrecken und Ausbruchlöcher (38) vorgesehen sind, die sich längs der Teilungsebenen von den Befestigeröffnungen (36) durch die Außenkanten der integralen Schenkel nach außen erstrecken, um vorbestimmte Auslaufstellen für die daraufhin geschaffenen Bruchflächen (29, 30, 32, 33) zu schaffen.

5. Verfahren zur Herstellung einer geteilten Lageranordnung (20) nach Anspruch 1, bei dem die geteilte Lageranordnung (20) eine Verbindungsstangen-Anordnung umfaßt.

6. Vorrichtung zum Ausführen eines Verfahrens, nach einem der Ansprüche 1 bis 5, dadurch gekennzeichnet, daß die Vorrichtung umfaßt eine Aufspannanordnung (50), die eine Körperklemmanordnung (51) und eine Deckelklemmanordnung (52), die relativ zueinander längs in Längsrichtung ausgerichteter Wege (54) in linearen Trenn- und Näherungsbewegungen bewegbar sind, und einen Brechstößel (55) enthält; wobei die Körperklemmanordnung (51) ein halbkreisförmiges Führungsstück (56) umfaßt, das mit einer körperseitigen Hälfte der Lagerzapfen-Aufnahmeöffnung (34) in Eingriff bringbar ist, und ein Paar Körperklemmelemente (58), die im betätigten Zustand an den Schenkeln (22, 24) des Körpers (21) angreifen, um den Körper unverdrehbar gegen das Führungsstück (56) zu klemmen; die Deckelklemmanordnung (52) ein halbkreisförmiges Führungsstück (59) umfaßt, das mit einer deckelseitigen Hälfte der Lagerzapfen-Aufnahmeöffnung (34) in Eingriff bringbar ist, und ein Deckelklemmelement (60), das im betätigten Zustand an den Schenkeln (26, 28) des Deckels (25) angreift, um den Deckel (25) unverdrehbar gegen das Führungsstück (59) zu klemmen; und der Brechstößel (55) einen Keil (62) enthält, der, wenn er durch einen Stoßmechanismus angetrieben ist, gegen die schrägen Seiten (63) von Einschnitten in den Führungsstücken (56, 59) wirkt, um den Deckel (25) schnell linear von dem Körper (21) abzutrennen.

Revendications

1. Procédé de fabrication d'un ensemble de palier en deux éléments (20) possédant un corps principal (21) en forme de berceau, comprenant des première

et deuxième branches (22, 24) et un chapeau de palier amovible (25) en forme de berceau, qui comprend des première et deuxième branches (26, 28) possédant des extrémités (29, 32) fixées respectivement en contact bout à bout avec des extrémités de formes complémentaires (30, 33) des première et deuxième branches (22, 24) dudit corps (21) pour définir une ouverture (34) de réception de la portée, ledit procédé consistant à former initialement le corps (21) et le chapeau (25) de l'ensemble de palier en un seul bloc, avec les extrémités de formes complémentaires (29-30, 32-33) des branches du corps et du chapeau formant bloc, ledit corps et ledit chapeau formant bloc de façon relativement fragile, au moins le long de plans de rupture (38, 39) sensiblement prédéterminés, qui définissent les extrémités des branches de part et d'autre de ladite ouverture (34), ledit corps (21) et ledit chapeau (25) ayant pratiquement leurs dimensions finales d'assemblage, ladite ouverture (34) étant centrée sur un axe (40) qui est continu dans ledit corps principal (21) et ledit chapeau (25), à peu près entre lesdits plans de rupture (38, 39), et à séparer le chapeau (25) du corps principal (21) en fracturant les branches formant bloc (22-26, 24-28) à peu près le long desdits plans de rupture (38, 39) de part et d'autre de ladite ouverture (34) pour former lesdites branches (26, 28, 22, 24) du chapeau (25) et du corps (21) en forme de berceau, lesdites premières et deuxième branches du chapeau (25) et du corps (21) constituant respectivement des première et deuxième paires qui peuvent s'accoupler au niveau desdits plans de rupture (38, 39), dans lequel la phase de fracture s'effectue en engendrant une tension d'un bord à l'autre des plans de rupture (38, 39) desdites branches formant bloc, en écartant à force le chapeau (25) et le corps principal (21) l'un de l'autre dans la direction longitudinale pour fracturer et séparer les extrémités (29-30, 32-33) des branches desdites paires au niveau de leurs plans de rupture respectifs tout en empêchant ledit chapeau (25) et ledit corps principal (21) de décrire des mouvements indésirés, caractérisé en ce que le procédé consiste, avant la phase de fracture, à retenir l'ensemble de palier monobloc dans un montage (50) de telle manière qu'il ne puisse se produire de déplacement notable dudit chapeau (25) par rapport audit corps (21) que dans une direction s'étendant selon un axe qui s'étend perpendiculairement auxdits plans de rupture (38, 39); et la phase de fracture s'effectue en écartant le chapeau (25) et le corps principal (21) à force linéairement tout en retenant continuellement ledit chapeau (25) et le corps principal pour s'opposer à toute rotation relative notable, en fracturant et séparant ainsi les extrémités des deuxdites paires de branches formant bloc au droit de leurs plans de rupture respectifs (38, 39) en un mouvement de séparation entre le chapeau (25) et le corps principal (21) qui est pratiquement linéaire, en évitant de cette façon toute flexion des branches

au niveau des plans de rupture et en produisant des surfaces de fracture (29-30, 32-33) de formes complémentaires sur les bords des branches qui entrent en prise, pour donner la possibilité de réassembler avec des formes complémentaires sans modification dimensionnelle notable de ces branches.

2. Procédé de fabrication d'un ensemble de palier en deux éléments (20) selon la revendication 1, dans lequel la phase consistant à écarter le chapeau (25) et le corps principal (21) à force en mouvement linéaire s'effectue en appliquant des forces de séparation au corps (21) et au chapeau (25) dans les directions normales à un plan qui réunit les plans de rupture (38, 39) des deux paires de branches, lesdites forces étant appliquées aux côtés opposés de ladite ouverture (34), entre les branches du corps (21) et celles du chapeau (25).

3. Procédé de fabrication d'un ensemble de palier en deux éléments (20) selon la revendication 1 ou 2, dans lequel on forme des encoches longitudinales (42, 44) le long des bords intérieurs des plans de rupture (38, 39) sur les deux côtés opposés de l'ouverture (34) avant la phase de fracture, pour amorcer la fracture et fixer positivement la position des bords intérieurs des extrémités séparées des branches (29, 30, 32, 33).

4. Procédé de fabrication d'un ensemble de palier en deux éléments (20) selon une quelconque des revendications précédentes, dans lequel les branches formant bloc sont munies d'ouvertures (36) de passage d'organes de fixation qui partent du chapeau (25) en pénétrant dans le corps (21) de part et d'autre de l'ouverture (34), et des trous d'arrêt de fracture (45) sont prévus, en s'étendant vers l'extérieur le long des plans de rupture, à partir des trous (36) de passage des organes de fixation, à travers les bords extérieurs des branches formant bloc, pour établir des lieux de terminaison prédéterminés pour les surfaces de fracture (29, 30, 32, 33) qui se produiront ensuite.

5. Procédé de fabrication d'un ensemble de palier en deux éléments (20) selon la revendication 1, dans lequel ledit ensemble de palier à deux pièces (20) est constitué par un ensemble de bielle.

6. Appareil pour la mise en oeuvre du procédé selon une quelconque des revendications 1 à 5, caractérisé en ce que ledit appareil comprend un montage (50) comprenant un ensemble (51) d'ablocage du corps et un ensemble (52) d'ablocage du chapeau pouvant se déplacer l'un par rapport à l'autre le long de glissières (54) alignées longitudinalement, en décrivant des mouvements linéaires d'écartement et de rapprochement, et un vérin de fracture (55); ledit ensemble (51) d'ablocage du corps comprend un pilote semi-circulaire (56) qui peut s'appliquer contre une moitié côté corps de ladite ouverture (34) de réception de la portée, et une paire d'éléments d'ablocage du corps (58) qui, lorsqu'ils sont actionnés,

s'appliquent contre les branches (22, 24) du corps (21) pour bloquer le corps contre ledit pilote (56) dans une position immobilisée en rotation; ledit ensemble (52) d'ablocage du chapeau comprend un pilote semi-circulaire (59) qui peut être appliqué contre une moitié côté chapeau de ladite ouverture (34) de réception de la portée, et un élément (60) de serrage du chapeau qui, lorsqu'il est actionné, s'applique contre les branches (26, 28) du chapeau (25) pour bloquer le chapeau (25) contre ledit pilote (59) dans une position immobilisée en rotation; et ledit vérin de fracture (55) comprend un coin (62) qui, lorsqu'il est entraîné par un mécanisme à impact, agit contre des côtés inclinés (63) d'évidements prévus dans les pilotes (56, 59) pour séparer rapidement le chapeau (25) du corps (21) par un mouvement linéaire.




Fig. 1




Fig. 2




Fig. 4




Fig. 3




Fig. 5

500 / 60 64 Dorn

